


Classification of Natural Weathering [Type of Panels 2 – EN 13523-19]

Panel Identification No & Description	Start of Exposure	Date of Inspection	Accumulative Time of Exposure (months)	Exposure Site & Corrosivity Category (EN ISO 12944-2)	Orientation of Exposed Panel
19KR013: Colorcoat Prisma® Textured, Anthracite, ZA255, CF79 Primer	21/08/2019	20/09/2023	48 months	BREST (France) Carbon Steel – C5 (Very High) Zinc – C3 (medium)	90° North
Average Edge Delamination (mm)		Damage on Bend		Blistering	
Conforms to RC5+ requirements		Conforms to RC5+ requirements		Conforms to RC5+ requirements	
Corrosion Resistance Category (as defined by EN 10169)					
The coil coated material ref 19KR013 fulfills RC5+ requirements according to EN 10169 standard.					

Brest, March 29 th , 2024	
Written by Déborah Tanguy 	Approved by Krystel Pélissier 